

TECHNICAL NOTE

Recommendations for AWWA C901 Service Tubes in Potable Water Applications



PPI TN-49
2025 Edition

Foreword

This technical note was developed and published with the technical help and financial support of the members of the Plastics Pipe Institute (PPI). These members have shown their commitment to developing and improving quality products by assisting standards development organizations in the development of standards, and also by developing design aids and reports to help engineers, code officials, specifying groups, contractors and users.

PPI has prepared this technical note as a service to the industry. The information in this note is offered in good faith and believed to be accurate at the time of its preparation, but is offered “as is” without any express or implied warranty, including WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Additional information may be needed in some areas, especially with regard to unusual or special applications. Consult the manufacturer or material supplier for more detailed information. A list of member manufacturers is available on the PPI website. PPI does not endorse the proprietary products or processes of any manufacturer and assumes no responsibility for compliance with applicable laws and regulations.

PPI intends to revise this technical note within 5 years, or sooner if required, from the date of its publication in response to comments and suggestions from users of the document. Please send suggestions for improvements to the address below. Information on other publications can be obtained by contacting PPI directly or visiting our website.

© 2025 **The Plastics Pipe Institute, Inc.**

<https://www.plasticpipe.org/>

TN-49, was first issued in June 2017 and was revised in September 2020 and June 2025

Table of Contents

1.0	Introduction.....	1
2.0	Background	1
3.0	Quick Selection Method.....	2
4.0	Specifying the PE Pipe Compound	3
5.0	Case Studies	3

List of Tables

Table 1:	TN-49 Quick Selection Table for AWWA C901	2
Table 2:	F_{size} Factor for use in TN-44 calculations for AWWA C901 Pipe and Tubing	3
Table 3:	Resistance to Disinfectants at Selected Utilities using PE4710 CC3	3

**RECOMMENDATIONS FOR
AWWA C901 SERVICE TUBES IN POTABLE WATER APPLICATIONS
PPI TN-49**

1.0 INTRODUCTION

On June 23, 2020, the American Water Works Association 263 Committee approved revisions to ANSI/AWWA C901-17 “Polyethylene (PE) Pressure Pipe and Tubing, ¾ In. (19 mm) Through 3 In. (76 mm), for Water Service.” The updated Standard was published in 2021. It requires the use of only PE4710 compounds with the highest oxidative resistance performance class, CC3. In addition, SDR 9 is the only allowed Dimension Ratio under AWWA C901.

Based on these AWWA C901 requirements, this PPI Technical Note provides a quick and simple guide for the selection of PE water service tubes for use in potable water applications with chlorine and chloramine disinfectant residuals. Users can compare their operating conditions to the Quick Selection Table to determine whether additional analysis is required. Most AWWA C901 users will find their operating environment readily satisfied by specifying SDR 9 tubes using compounds with CC3, and will achieve projections of 100 year+ resistance to the disinfectants.

This Technical Note addresses chlorine and chloramine usage as a secondary disinfectant. Chlorine Dioxide (ClO₂) as a secondary disinfectant residual is not covered by this guidance. At this time, PE pipe is not recommended with these ClO₂ applications because further research is needed to determine performance. Refer to the pipe manufacturer for ClO₂ applications.

2.0 BACKGROUND

Polyethylene (PE) pipes intended for potable water applications contain additives to provide resistance to the long-term oxidizing effects of water disinfectants. Research programs conducted on PE piping compounds resulted in the development of a model that projects the performance of PE pipes in long-term chlorinated potable water service.¹ The model is based on accelerated testing of many PE compounds in accordance with ASTM F2263² and the model allows the projection of the performance of PE pipes to specific end-use service conditions.

PE pipe compounds specified for potable water applications are categorized for oxidative resistance performance in accordance with ASTM D3350³ based on ASTM F2263 testing. Per the revised AWWA C901 (2021), the acceptable oxidative resistance category is CC3. As such, PPI TN-49 guidance is also based on the use of the highest category PE compound, CC3.

¹ Jana Technical Report, “JP 916: Jana Mode 3 Shift Functions”, March 2012

² ASTM F2263, *Test Method for Evaluating the Oxidative Resistance of Polyethylene (PE) Pipe to Chlorinated Water*, West Conshohocken, PA

³ ASTM D3350, *Standard Specification for Polyethylene Plastics Pipe and Fittings Materials*, West Conshohocken, PA

3.0 QUICK SELECTION METHOD

The service life of a water tubing system depends on many factors. The long-term resistance to disinfectants is one of these factors. To simplify the selection of PE service tubes in the vast majority of applications, PPI developed the TN-49 Quick Selection Table (Table 1 below) to provide users with an easy to assess 100-year oxidative resistance pipe solution.

Users specifying PE compounds with CC3 categorization and with operating conditions within Table 1 designated ranges have projected resistance to disinfectant conditions of at least 100 years.

For example:

- Utility A, using a PE 4710 CC3 compound, has an average annual water temperature of 60°F, an average **chlorine** residual of 1.1 ppm, average pH of 7.4, and an average working pressure of 125 psi. The chlorine residual and pH values are within the Quick Selection Table ranges, so the Quick Selection method applies and confirms the resistance to disinfectant conditions of at least 100 years for all AWWA C901 sizes.
- Utility B, using a PE 4710 CC3 compound, has an average annual water temperature of 73°F, an average **chloramine** residual of 2.2 ppm, average pH of 6.8, and an average working pressure of 250 psi. Table 1 indicates that there are no limits on chloramine residual and pH values. Thus, the Quick Selection Table confirms the resistance to disinfectant conditions of at least 100 years for all AWWA C901 sizes.

Table 1: TN-49 Quick Selection Table for AWWA C901

PE Compound Oxidative Resistance Category	PE 4710 CC3				
Average Annual Water Temperature *	≤ 73 °F				
Residual Disinfectant Type	Chloramine	Chlorine			
Average Disinfectant Residual	No limit	≤ 2.0 ppm			
Average pH	No limit	≥ 7.0			
Nominal Pipe Size (inches)**	≥ ¾	¾	1	2	3
Average Working Pressure (psig)	≤ 250	≤ 142	≤ 152	≤ 181	≤ 202
Projected Oxidative Resistance under the specific operating conditions	≥ 100 years				

* The Average Annual Water Temperature (AAWT) is a weighted average of the daily water temperature, not the highest temperature observed in the system, experienced by the pipe or tubing. In situations where the service lines are buried just beneath the pavement, a higher water temperature estimate for the AAWT may be required.

** Dimensional Ratio SDR 9 per AWWA C901

Users with operating conditions that fall outside the designated ranges in Table 1 should conduct an additional analysis per [PPI TN-44](#)⁴ using factors for AWWA C901 sizes (i.e. F_{size}) specified in Table 2 (TN-49), or refer to www.HDPEapp.com for this analysis.

Table 2: F_{size} Factor for use in TN-44 calculations for AWWA C901 Pipe and Tubing

Nominal Pipe Size (inches)	¾	1	1.25	1.5	2	3
F _{size}	0.22	0.28	0.34	0.40	0.52	0.76

4.0 SPECIFYING THE PE PIPE COMPOUND

For potable water applications, the specifier should append the required chlorine category (CC3) class in accordance with ASTM D3350 cell classification. Examples of call-outs for PE4710 compounds are provided below:

- PE 445574E CC3 - for colored pipe with UV stabilizer
- PE 445574C CC3 - for black pipe with a minimum of 2% carbon black

5.0 CASE STUDIES

Table 3 (below) shows case studies under the specific operating conditions for 10 utilities as analyzed per PPI TN-49. In all these applications, AWWA C901 PE4710 pipe is projected to provide at least 100-year resistance to chlorine and chloramine residual disinfectants; note that these systems include utilities with high average working pressure (Colorado, 250 psi), high average temperature (Florida, 79 °F) and high average Cl₂/Low pH (Nevada, 1.1 ppm / 7.8). For conditions outside the TN-49 Quick Selection Table, [PPI TN-44](#) was used to confirm projected performance of at least 100 years.

Table 3: Resistance to Disinfectants at Selected Utilities using PE4710 CC3

Utilities Location	IN-1	CA-1	FL	TX	IN-2	NC	CO	CA-2	NV	MI
Residual Disinfectant Type	Chloramine*				Chlorine					
Nominal Size	¾" to 3" (SDR9 per AWWA C901)									
Average Disinfectant Residual (ppm)	1.6	1.9	1.4	2.5	1.4	0.9	0.5	0.9	1.1	1.5
Average pH	7.7	9.0	9.3	7.3	8.8	8.6	7.9	7.9	7.8	8.0
Average Annual Water Temperature (°F)	57	61	79	72	54	68	50	64	70	48
Average Working Pressure (psig)	70	65	70	125	70	70	250	77	100	100
Projected Oxidative Resistance under the specific operating conditions	≥ 100 years									

* In 2014, it was “estimated that approximately 30% of municipal water utilities use monochloramine for residual disinfection ... and that number is expected to increase to 60% as more-stringent DBP [Disinfectant By-Product] regulations go into effect...” Ref: Nagisetty, R., Rockaway, T. and Willing, G., *Drinking Water Quality Concerns from Chloramine-Induced Degradation of Elastomeric Compounds*, AWWA Journal, Sep. 2014.

⁴ PPI Technical Note 44, “Long Term Resistance of AWWA C906 Polyethylene (PE) Pipe to Potable Water Disinfectants”, Plastics Pipe Institute, Inc., Irving, Texas, USA